



809

2K Plasticizer Matt

Description:

809 2K Plasticizer Matt is a universal plasticizer for all MS and VOC topcoat systems. It is suitable for General filler and plastic finishes. 809 demonstrate high long-term elasticity.

Preparation:

- Can be used for all car plastic panels.
- Add 15% of plasticizer to topcoats, clearcoats and fillers with medium and hard plastics.
- Add 30% of plasticizer to topcoats, clearcoats and fillers with soft plastics.

addition of 809 to 683 clear	Gloss level at 60 degrees
50%	75-85%
100%	65-75%
150%	50-60%
200%	10-20%

Flash Point: 27° C /80.6° F

Specific Gravity: 1.032 g/cm³

Solids Content: 46.8 Weight %

Cleaning the Equipment: Clean after use with General cleaning thinner.

IMPORTANT REMARKS:

- General 2K Plasticizer Matt must be included before the addition of 2K hardener.
- To optimize the sanding properties the plasticized fillers should be dried 45 min/60-65 ° C panel temperatures. 809 may be added in a maximum proportion of 1:1 for maximum plasticizing effect.
- When 809 is added to General 2K systems, it slows down the drying.

SAFETY:

Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your convenience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.

Note: General recommends that our products not be used under 10°C. Usage below 10°C can result in extended drying times or product failure.

General Paint Co.

P.O. Box: 7623 Beirut – Lebanon – Tel.: 09 925991/2 – Fax: 09 925993 – E-mail:Info@generalpaint.biz