




7500 – Express L.E. Clear

Description:


A VOC compliant, UHS, high quality, two component clearcoat with good vertical stability, short drying times, excellent gloss in combination with very good polishability.

Suitable Substrates:

- “General” GenRock Basecoat.
- “General” Gen₂O Basecoat.



Mix 2:1 with General L.E Hardener series (H820, H920, H960 etc...)
Potlife 60 min / 20 °C (68°F)




18-20 sec / DIN 4 mm / 20 °C (68 °F)



Compliant 1.3 – 1.4 mm
2.0 – 2.5 bar inlet pressure
HVLP 1.3 - 1.4 mm; 0.7 bar at the air-cap



1 clinging coat + 1 full coat
50- 60 microns per coat



5-10 minutes at 20 °C (68 °F)



20-25 min. at 60 °C (140 °F) panel temperature.



10 – 12 min. Short Wave
The object should be maintained at greater than 60cm from source



Wear suitable protection



7500 – Express L.E. Clear

Flash Point: 24°C (74 °F)

Solids Content: 58 % by weight – ready to spray

VOC (2004/42/EC): 2004/42/IIB (d) (420)420. The EU limit value for this product (product category IIB.d) in ready to use form is max 420g/ltr. The VOC content of this product in ready for use form is max. 420 g/l.

Coverage: 9-10 m²/l at 50 micron film thickness (theoretical)

SDS: See the safety data sheet